

Product properties

Format		1170 x 120 x 13 mm	2200* x 185 x 13 mm	2380* x 233 x 13 mm
Top layer		≥ 2.5 mm		
Packaging	Pack	12 Elements 1,685 m ² / 11,532 kg	9 Elements 3.663 m ² / 26.163 kg	6 Elements 3,327 m ² / 23,000 kg
	Pallet	30 Packs 50,544 m ² / 345,96 kg	32 Packs 117,216 m ² / 837,216 kg	36 Packs 119,772 m ² / 830,000 kg
Guarantee (according to Parador guarantee conditions)			25 years (private use) 10 years (commercial use)	
Notes			*1 joint length permitted per package - cleaning and maintenance see instructions - technical changes reserved	

Product labelling



Tolerances (EN 13489)

Admissible difference in length (± 0.1 %)	± 0.05 %
Admissible difference in width (± 0.2 mm)	± 0.1 mm
Squareness of the element (≤ 0.2 %)	≤ 0.05 %
Longitudinal curvature along the element (≤ 0.1 %)	≤ 0.05 %
Transverse curvature across the width (≤ 0.2 %)	≤ 0.08 %
Height differences of elements (≤ 0.2 mm)	≤ 0.18 mm
Moisture content at the time of first delivery (5-9%)	6 – 8 %

Classification general product features

	Test method	Rating
Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat
Effect of a furniture leg	EN 424	No visible changes
Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN ISO 10456	0.087 m ² *K/W
Formaldehyde (E1 = 0.1 ppm)	EN 16516	≤ 0.05 ppm
Acoustical - Impact noise reduction	ISO 717-2	18 dB (with Akustik-Protect 100)
Disposal		EAK-Code-number 20 01 38

Classification surface characteristics

		Test method	Rating	
			Lacquer	Natural oiled plus
	Slip resistance	EN 13893	μ ≥ 0.47	μ ≥ 0.49
		CEN/TS 15676	29 SRT (SRV wet)	99 (USRV)
			51 SRT (SRV dry)	
	Reaction to fire, click-installation as a floating floor	EN 13501-1	D _{fl} s1	
	Reaction to fire, installation by all-over adhesion	EN 13501-1	D _{fl} s1	
	Chemical resistance	EN 13442:2023 Annex B	Category 5	Category 5
	Bond strength / Cross cutting test	ISO 2409	0	n.n.
	Slip resistance, inclined plane	EN 16165, Annex B	R 9	R 10

Free sorting according to EN 13489	
Assortment:	3-strip
Characteristics according to EN 1310:	Upper side of the lamella
Type of wood:	Oak
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE
Shortcut / grade (internal):	ER-L-EI Akt.
	Version 4 2019
Grade:	Rustikal
Sound sapwood	permitted (also discoloured)
Knot (intergrown)	permitted: up to 30 mm
Falling out knot	permitted: up to 20 mm
Pinkknots	permitted
Filling	permitted
Slight cracks / hairline cracks	permitted
Bark pocket	permitted
Lightning cracks	permitted
Slope of grain	no criterion
Healthy heart	-
Medullary ray	permitted
Discoloration, colour variation	permitted: all colours / slight discolouration
White streaks	permitted
Pilling sticks marking	not permitted
Biodeterioration (EN 1311)	not permitted
Non-visible parts	
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.	
Comment	
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.	

Changed:	QMB	File name:	PA_TDS_Parkett_Classic-3025_Anhang_EN_20231201
Date:	01.08.2013	Update:	https://parador.de/en/pcms/downloads/downloadfile/file_id/864/
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:		01.12.2023	Page 1 of 3

Free sorting according to EN 13489			
Assortment:	Wide plank / Extra-sized wideplank		
Characteristics according to EN 1310:	Upper side of the plank		
Type of wood:	Oak		
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE		
Shortcut / grade (internal):	GÜ_LHD-EI		
	Version 4 2022		
Grade:	Classic	Rustikal	Character
Sound sapwood	not permitted	permitted	not permitted
Knot (intergrown)	permitted: up to 30 mm	permitted: up to 80 mm	permitted
Falling out knot	permitted: up to 25 mm	permitted: up to 60 mm	permitted: up to 80 mm
Pinknots	permitted	permitted: cluster of knots	
Filling	permitted		
Slight cracks / hairline cracks	permitted		
Bark pocket	not permitted	permitted	
Lightning cracks	permitted		
Slope of grain	no criterion		
Healthy heart	permitted		
Medullary ray	not permitted	permitted	
Discoloration, colour variation	permitted: slight colour variations	permitted: all colours	permitted: all colours / inlets in all colours and dimensions
White streaks	permitted		
Pilling sticks marking	not permitted		
Biodeterioration (EN 1311)	not permitted		
Non-visible parts			
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.			
Comment			
Maximum 3% of planks are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.			

Changed:	QMB	File name:	PA_TDS_Parkett_Classic-3025_Anhang_EN_20231201	
Date:	01.08.2013	Update:	https://parador.de/en/pcms/downloads/downloadfile/file_id/864/	
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.12.2023	Page 2 of 3

Free sorting according to EN 13489			
Assortment:	Wide strip		
Characteristics according to EN 1310:	Upper side of the plank		
Type of wood:	Oak		
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE		
Shortcut / grade (internal):	ER-TT0-EI		GÜ_LHD-EI
	Version 2 2018		Version 4 2022
Grade:	Natur	Living	Living Plus
Sound sapwood	not permitted	permitted	not permitted
Knot (intergrown)	permitted: up to 15 mm	permitted: up to 30 mm	permitted: up to 50 mm
Falling out knot	not permitted	permitted: up to 10 mm	permitted: up to 25 mm
Pinkknots	permitted	permitted: cluster of knots	
Filling	permitted		
Slight cracks / hairline cracks	not permitted	permitted	
Bark pocket	not permitted		
Lightning cracks	permitted		
Slope of grain	no criterion		
Healthy heart	not permitted		
Medullary ray	permitted		
Discoloration, colour variation	permitted: slight colour variations		
White streaks	not permitted	permitted	
Pilling sticks marking	not permitted		
Biodeterioration (EN 1311)	not permitted		
Non-visible parts			
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.			
Comment			
Maximum 3% of planks are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.			

Changed:	QMB	File name:	PA_TDS_Parkett_Classic-3025_Anhang_EN_20231201
Date:	01.08.2013	Update:	https://parador.de/en/pcms/downloads/downloadfile/file_id/864/
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:		01.12.2023	Page 3 of 3